

# Comprehensive Guide to Biomass Briquetting: Technology, Engineering, and Global Practices

Published: April 1, 2026 | Index ID: #339

The global transition toward sustainable energy systems has placed biomass at the center of the renewable energy discourse. While loose biomass residues—such as agricultural waste, forest residues, and industrial wood waste—are abundant, their inherent physical properties often limit their utility as a primary fuel source. High moisture content, low bulk density, and irregular shapes make transportation, storage, and combustion inefficient. To overcome these logistical and thermal hurdles, **biomass briquetting**, or densification, has emerged as a critical technological intervention. This process transforms loose, low-density organic matter into high-density, energy-concentrated fuel units known as briquettes.

## The Fundamental Role of Densification in Bioenergy

Biomass densification is a thermomechanical process that involves the application of pressure to loose organic materials, often in the presence of heat. The primary objective is to increase the **volumetric calorific value** of the fuel. When loose residues are compressed, the air trapped between the particles is forced out, and the material undergoes physical and chemical changes that result in a solid, cohesive block. Based on the seminal work of **P.D. Grover and S.K. Mishra (1996)**, the success of briquetting depends on the interplay between the raw material's characteristics and the mechanical force applied.

The significance of this technology extends beyond mere fuel production. It addresses the **circular economy** by converting waste into wealth, reduces the pressure on forest resources by providing an alternative to traditional firewood, and significantly lowers the carbon footprint of industrial thermal applications. In many developing regions, biomass briquettes serve as a direct substitute for coal and charcoal, offering a cleaner combustion profile and improved thermal efficiency.

## The Science of Binding: Lignin and Thermal Transitions

One of the most critical aspects of biomass briquetting is the **binding mechanism**. Biomass is composed primarily of cellulose, hemicellulose, and lignin. Lignin is a complex organic polymer that acts as the "glue" within the plant's cell walls. Under high pressure and temperatures ranging from 140°C to 200°C, lignin reaches its **glass transition temperature**. At this point, it softens and flows, acting as a natural binder that coats the cellulose fibers. Once the pressure is released and the material cools, the lignin solidifies, creating a high-strength physical bond that maintains the briquette's structural integrity without the need for external chemical additives.

## Technical Specifications and Raw Material Requirements

Not all biomass is immediately suitable for briquetting. The physical and chemical properties of the feedstock determine the quality of the final product and the energy required for the densification process. Key parameters include:

- **Moisture Content:** Ideally, the moisture content of the feedstock should be between 8% and 15%. If the moisture is too high, steam pockets form during compression, causing the briquettes to explode or crumble. If it is too low, the lignin will not soften sufficiently, resulting in poor binding.
- **Particle Size:** Uniformity in particle size (typically 6mm to 8mm) is essential for consistent densification. Larger

particles may create structural weaknesses, while overly fine dust can increase friction and wear on machine components.

- Ash Content: Higher ash content (e.g., in rice husks) can lead to slagging in boilers and increased wear on the briquetting dies.

- Bulk Density: The initial density of the feedstock dictates the compression ratio required to achieve the desired final density of 1,000 to 1,200 kg/m<sup>3</sup>.

### Comparison of Common Biomass Feedstocks

The following table illustrates the variation in properties across common agricultural and forest residues used in the briquetting process:

| Feedstock Type  | Calorific Value (kcal/kg) | Ash Content (%) | Moisture Content (Initial %) | Suitability                     |
|-----------------|---------------------------|-----------------|------------------------------|---------------------------------|
| Sawdust         | 4,200 - 4,700             | 1.0 - 2.0       | 25 - 50                      | Excellent (Low Ash)             |
| Rice Husk       | 3,000 - 3,500             | 15.0 - 20.0     | 10 - 15                      | Moderate (High Abrasiveness)    |
| Groundnut Shell | 4,300 - 4,500             | 3.0 - 4.5       | 8 - 12                       | Excellent (Natural Oil content) |
| Coffee Husk     | 3,800 - 4,100             | 2.0 - 4.0       | 10 - 12                      | Good                            |
| Wheat Straw     | 3,500 - 3,900             | 5.0 - 8.0       | 15 - 30                      | Requires Pre-processing         |

## Classification of Briquetting Technologies

The engineering behind briquetting has evolved into several distinct categories, each suited for different scales of production and feedstock types. The two most dominant industrial methods are **Screw Press Extrusion** and **Piston Press Compaction**.

### 1. Screw Press Extrusion Technology

In a screw press, the biomass is continuously fed into a hopper and conveyed by a rotating screw through a heated tapered die. The combination of the screw's mechanical force and the external heat applied to the die causes the lignin to flow and bond the material. This method produces a **hollow-core briquette**, which provides a larger surface area for more efficient combustion.

- Advantages: High-quality, uniform density; high calorific value per unit volume; the hollow center facilitates better airflow during burning.
- Disadvantages: High power consumption and significant wear on the screw (requiring frequent maintenance/re-building).

### 2. Piston Press Compaction (Mechanical and Hydraulic)

This technology uses a reciprocating piston to ram the biomass into a die. In **mechanical piston presses**, a flywheel provides the momentum, while **hydraulic presses** use fluid pressure. This is a "punching" process rather than a continuous extrusion.

- Advantages: Capable of handling larger capacities; lower maintenance costs compared to screw presses; produces solid "log-style" briquettes.
- Disadvantages: The density may be slightly lower than screw-pressed briquettes; the exterior is not charred, making it more susceptible to moisture absorption if not stored correctly.

### 3. Roller Press (Pelletizing)

While often used for pellet production, larger roller presses can produce pillow-shaped briquettes. This is typically used for charcoal dust or inorganic materials where high binding pressure is less critical than throughput.

## The Industrial Briquetting Workflow: A Step-by-Step Analysis

Producing high-quality biomass briquettes requires a synchronized sequence of mechanical operations. Failure at

any stage of the pre-treatment can compromise the quality of the final fuel.

### Step 1: Collection and Sorting

The raw material is gathered and screened to remove contaminants such as stones, metal fragments, and plastics. Foreign objects can cause catastrophic failure in high-speed hammers or extrusion screws.

### Step 2: Size Reduction (Crushing/Grinding)

Most residues, like corn stalks or large wood chips, are too bulky for the briquetting die. **Hammer mills** are used to grind the material into a consistent particle size, typically 3mm to 10mm. This increases the surface area for lignin bonding.

### Step 3: Drying

As mentioned previously, moisture is the enemy of densification. **Flash dryers** or **rotary drum dryers** use hot air (often generated by burning a small portion of the biomass) to reduce the moisture content to the 10-12% threshold. This is often the most energy-intensive part of the entire process.

### Step 4: Densification

The conditioned material is fed into the briquetting machine. In a screw press, the material is heated to approximately 160°C. The friction and pressure increase the density from roughly 150 kg/m<sup>3</sup>; (loose) to over 1,100 kg/m<sup>3</sup>; (densified).

### Step 5: Cooling and Packaging

Emerging briquettes are extremely hot and slightly plastic. They must be transported along a **cooling conveyor** to allow the lignin to set and the internal steam to dissipate. Once cooled, they are cut to length and packaged in moisture-proof bags for distribution.

## Engineering Comparison: Screw Press vs. Piston Press

---

Choosing the right technology depends on the intended end-use and the available capital expenditure. The following matrix provides a technical comparison:

| Feature                | Screw Press (High Pressure)   | Piston Press (Mechanical)     |
|------------------------|-------------------------------|-------------------------------|
| Briquette Shape        | Cylindrical with center hole  | Solid cylindrical / Log       |
| Briquette Density      | 1.2 - 1.4 g/cm <sup>3</sup> ; | 1.0 - 1.2 g/cm <sup>3</sup> ; |
| Combustion Quality     | Excellent (Hollow center)     | Good                          |
| Maintenance Frequency  | High (Screw wear)             | Low to Medium                 |
| Operating Mode         | Continuous Extrusion          | Intermittent/Ramming          |
| External Heat Required | Yes (Die heating)             | No (Frictional heat only)     |

## Economic and Environmental Impact Analysis

The adoption of biomass briquetting offers significant macro-economic benefits, particularly in agrarian economies. By densifying residues, the **logistics costs** associated with biomass are reduced by up to 80% due to the improved volume-to-weight ratio. This makes it feasible to transport biomass over longer distances to reach industrial hubs.

From an environmental perspective, briquettes are **carbon neutral**. The carbon dioxide emitted during combustion is equivalent to the amount absorbed by the plant during its growth cycle. Furthermore, replacing coal with biomass briquettes significantly reduces sulfur dioxide (SO2) and nitrogen oxide (NOx) emissions, which are primary contributors to acid rain and respiratory issues.

### Mathematical Formula for Energy Density Improvement

The efficiency of the briquetting process can be quantified by the Energy Density Ratio (EDR):

$$EDR = (D_b * CV_b) / (D_l * CV_l)$$

Where:  
 $D_b$  = Density of the briquette (kg/m<sup>3</sup>);  
 $CV_b$  = Calorific value of the briquette (MJ/kg)  
 $D_l$  = Density of the loose biomass (kg/m<sup>3</sup>);  
 $CV_l$  = Calorific value of the loose biomass (MJ/kg)

Typically, the EDR for sawdust-to-briquette conversion is between 7 and 10, indicating a massive increase in energy concentration per cubic meter of storage space.

## Common Operational Challenges and Solutions

Operating a biomass briquetting plant requires constant monitoring of variables. Below are common failure modes and their engineering solutions:

### 1. Jamming of the Die

**Cause:** Moisture content is too low or the feedstock contains too much silica (sand).**Solution:**Introduce a steam conditioning step or implement a rigorous screening process to remove mineral contaminants.

### 2. Briquettes Cracking (Honeycomb Effect)

**Cause:** High moisture content or insufficient pressure.**Solution:**Recalibrate the dryer settings or inspect the screw/piston for wear that may be reducing the compression force.

### 3. Excessive Smoke During Combustion

**Cause:** Incomplete carbonization or high moisture in the center of the briquette. **Solution:** Ensure a longer cooling time and check the temperature of the extrusion die to ensure proper thermal transition of the surface lignin.

## Future Horizons: Advanced Densification and Torrefaction

---

The next frontier in biomass briquetting is the integration of **torrefaction**. Torrefaction is a mild pyrolysis process (200&deg;C - 300&deg;C) performed in an oxygen-free environment. When biomass is torrefied before briquetting, the resulting "black briquettes" have properties very similar to coal. They are hydrophobic (water-resistant), have an even higher calorific value, and are easier to grind. This technology is currently being scaled for co-firing in large-scale coal power plants to meet carbon reduction targets.

Furthermore, research is expanding into **hybrid briquettes**, where sewage sludge or charcoal fines are mixed with agricultural residues. This not only solves a waste disposal problem but also creates a fuel with customized combustion characteristics tailored for specific industrial boilers.

The transition from traditional, inefficient biomass use to modern briquetting technology represents a pivotal shift in renewable energy management. By applying the principles of engineering and thermodynamics to organic waste, societies can create a reliable, high-energy fuel source that supports industrial growth while adhering to environmental safeguards. As documented by researchers like P.D. Grover, the technical path is clear: through proper pre-treatment, the right choice of machinery, and a deep understanding of the material science behind lignin binding, biomass briquetting stands as a cornerstone of the global bioeconomy.

Ultimately, the success of a briquetting enterprise relies on the balance between technical precision and local resource availability. As energy prices fluctuate and carbon taxes become more prevalent, the economic viability of densified biomass continues to strengthen, making it an indispensable component of the 21st-century energy mix. The evolution from loose, difficult-to-handle residues to uniform, high-performance briquettes is not just a change in form, but a transformation in energy potential.

## Baca Juga (Artikel Terkait)

---

- [Comprehensive Engineering Guide to Water Turbines: Design, Classification, and Operational Dynamics](http://www.alghafgolden.com/comprehensive-engineering-guide-water-turbines-design-classification.pdf)

URL: <http://www.alghafgolden.com/comprehensive-engineering-guide-water-turbines-design-classification.pdf>

- [The Engineering Evolution of Suzlon Wind Turbines: A Technical Deep Dive into Modern Renewable Solutions](http://www.alghafgolden.com/suzlon-wind-turbine-engineering-technical-analysis.pdf)

URL: <http://www.alghafgolden.com/suzlon-wind-turbine-engineering-technical-analysis.pdf>

- [A Technical Deep Dive into Community Solar: Utility, Private, and Non-profit Sponsorship Models](http://www.alghafgolden.com/technical-guide-community-solar-utility-private-nonprofit-models.pdf)

URL: <http://www.alghafgolden.com/technical-guide-community-solar-utility-private-nonprofit-models.pdf>

- [Advanced Simulation Modeling for Parabolic Trough Solar Power Plants: A Comprehensive Technical Engineering Guide](http://www.alghafgolden.com/parabolic-trough-solar-power-plant-simulation-modeling.pdf)

URL: <http://www.alghafgolden.com/parabolic-trough-solar-power-plant-simulation-modeling.pdf>

Tags: #Biomass Briquetting #Bioenergy #Densification #P.D. Grover #Sustainable Fuel #Industrial Engineering











